

Product Data Sheet

PRODUCT DESCRIPTION:

Van Sickle® Asphalt Aluminum Paint is a blend of our quality pigments and long wearing asphalt. This product is designed to provide superior long term protective results when properly applied. Developed to meet rigid performance requirements for durability and service, it produces a tough water and weather resistant film that will provide superior protection from rust and corrosion. This Van Sickle® Aluminum Paint meets or exceeds the quality of most equally priced aluminum paints on the market.

TYPICAL USES:

Van Sickle® Asphalt Aluminum is designed for lightly rusted or dull galvanized metal. Used primarily on roofs, Van Sickle® Asphalt Aluminum is not a roofing material for repair or replacement of an existing roof. This coating serves as a sealer and heat reflector as well as a cosmetic coating. Van Sickle® Asphalt Aluminum is ideal For Use On wood, metal or masonry surfaces. It can also be applied as a sidewall coating on industrial cinder block construction. Do Not Apply this product on drywall, plaster or plastic.

BASES & COLORS:

610 Asphalt Aluminum

PHYSICAL PROPERTIES:

PRODUCT NUMBER:	610
GENERAL TYPE:	Asphalt Aluminum;
COLOR:	Aluminum
GLOSS:	N/A @ 60°
SOLIDS BY WEIGHT:	43.7%
SOLIDS BY VOLUME:	36.6%
THEORETICAL COVERAGE @ 1 MIL DFT:	587Sq.Ft/Gal
RECOMMENDED DFT:	1.5 – 2.0mils DFT
VISCOSITY @ 78°F:	28-32 sec #2 Ford cup
WEIGHT PER GALLON:	7.4-7.5lbs.
FLASH POINT:	102°F
VOC:	500 G/L

SURFACE PREPARATION:

Proper surface preparation is the most important variable in determining the service life of a coating. For best results, all surfaces must be clean, dry and free from wax, oil, grease, dirt, mildew, loose rust, and any other contaminants. Repair cracks, breaks and open seams. On new wood or badly weathered wood, a primer coat is recommended. A primer coat is not needed on galvanized metal surfaces.

APPLICATION:

Apply by natural bristle brush, roller or spray. For best results, use spray application. Do Not Thin; use as is from the container. Do not add oils or any other paints to this product. Before and during application, stir the paint thoroughly from the bottom of the can with an upward motion, scraping the bottom to avoid pigment settling.

ENVIRONMENTAL VARIABLES:

Apply only when surface and air temperatures are between 50° and 90°F. Avoid painting on hot days, in direct sunlight or late in the day when dew is likely to form. Cool, wet, humid or over-applied coatings can greatly decrease a thorough cure and interfere with proper film formation.

Dry-Times:

Drying time for this product will be approximately 24 hours to touch, and may be recoated after 48 hours under ideal drying conditions.

CLEAN-UP:

Clean up all tools and equipment with Mineral Spirits before paint is allowed to dry. To avoid spontaneous combustion during storage, soak soiled rags and waste immediately after use in a water-filled closed metal container.



610

Exterior Oil
Asphalt Aluminum



Product Data Sheet

CAUTIONS:

For exterior use only,
Do not take internally,
Use with adequate ventilation,
KEEP OUT OF REACH OF CHILDREN

***WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

For additional Product Information or Safety Data Sheets, please call 800-677-2468, 8:00-5:00 CST Mon.-Fri.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Van Sickle Paint does not control the application of its products, or the condition of the surfaces to which they are applied, Van Sickle Paint's liability will under no circumstances exceed replacement of the product.

